

Decorative Wall & Ceiling Linings

PRODUCT DATA SHEET

GP General Purpose Interior TIMBER



Spruce

Profiles

VJ/ Regency.

Description

Norway Spruce is a common softwood found in Europe and North America and is often referred to as deal or white wood. It is valued for its flexibility, durability, lightness, extended length, and straightness.

Visual Features

The sapwood of this species is generally white to pale yellow, contrasting with the brown to reddish-brown hues of the heartwood. Prominently marked growth rings are defined by the denser summer wood. Spruce possesses a relatively fine texture, and its grain is typically straight..

Applications

Easycraft General Purpose Interior Timbers are designed for interior walls and ceiling lining applications.



Fire Hazard Indices

(Typically achieved when tested to AS/NZS 1530.3)

Indices	Result
Spread of Flame	9
Smoke Development Index	4

Fire Test Results

Classification	Result
Group Number (AS 5637)	3
Average Specific Extinction Area	<250 m ² /kg



Properties

Specifications	Result
Density	470 Kg/m ³
Specific Gravity	12%
Hardness (Janka)	2.14 kN
Modulus of Rupture	66 Mpa
Modulus of Elasticity	8.2 GPa
Radial Shrinkage	1.9 %

Specifications	Result
Tangential Shrinkage	5 %
Durability in Ground	0-5 years
Durability Above Ground	0-7 years
Susceptible to Lyctid Borer	No
Termite Resistance	Not Resistant
Resistance to Split (Nailing)	Satisfactory

Specifications	Result
Resistance to Split (Screwing)	Satisfactory
Gluing	Satisfactory
Machining	Satisfactory
Finish	Satisfactory
Stability	Satisfactory
Growing Region	Europe

Contact Details

For further information on this product, contact:
1300 650 787 sales@porta.com.au easycraft.com.au

f @easycraftpanels @easycraft.panels

Easycraft is a brand of Porta Products Pty Ltd.
www.porta.com.au

Disclaimer

Whilst the information contained in this document is based on data which, to the best of our knowledge, was accurate and reliable at the time of preparation, we can accept no responsibility for errors and omissions. The provision of this information should not be construed as a recommendation to use any of our products in violation of any patent rights or breach of any statute or regulation. Users are advised to make their own determination as to the suitability of this information in relation to their particular purposes and specific circumstances. Since the information contained in this document may be applied under condition beyond our control, we can accept no responsibility for any loss or damage caused by any person acting or refraining from action as a result of this information.