

Decorative Wall & Ceiling Linings

PRODUCT DATA SHEET

GP General Purpose Interior TIMBER



easy^{craft}

Tasmanian Oak

Profiles

Riverine, Cirque, Strata, Groove, Pinnacle, Shade, Wave, Isthmus, DAR.

Description

A mixture of similar Eucalyptus species; e.delegatensis, e.obliqua and e.regnans, grown in Tasmania. Resilient and dense, Tasmanian Oak is an attractive and versatile timber for a wide range of applications.

Visual Features

Light in colour varying from straw to reddish brown with shades of cream and pink. Tasmanian Oak is uniform and smooth in texture with a straight even grain. Natural variations in grain, colour and texture are characteristics of the species. Gum veins and fiddleback are common features. After drying the timber remains very stable.

Applications

Easycraft General Purpose Interior Timbers are designed for interior walls and ceiling lining applications.



Fire Hazard Indices

(Typically achieved when tested to AS/NZS 1530.3)

Indices	Result
Spread of Flame	8
Smoke Development Rate	<750

Fire Test Results

Classification	Result
Group Number	3
Average Specific Extinction Area	<250 m ² /kg



Properties

Specifications	Result
Density	650 Kg/m ³
Specific Gravity	0.68
Hardness (Janka)	5.7 kN
Modulus of Rupture	110 Mpa
Modulus of Elasticity	17 GPa
Radial Shrinkage	6.6 %

Specifications	Result
Tangential Shrinkage	13.3 %
Durability in Ground	0-4 years
Durability Above Ground	0-3 years
Susceptible to Lyctid Borer	No
Termite Resistance	Not Resistant
Resistance to Split (Nailing)	Good

Specifications	Result
Resistance to Split (Screwing)	Good
Gluing	Good
Machining	Good
Finish	Good
Stability	Good
Growing Region	Tasmania

Contact Details

For further information on this product, contact:
1300 650 787 sales@porta.com.au easycraft.com.au

f @easycraftpanels @easycraft.panels

Easycraft is a brand of Porta Products Pty Ltd.
www.porta.com.au

Disclaimer

Whilst the information contained in this document is based on data which, to the best of our knowledge, was accurate and reliable at the time of preparation, we can accept no responsibility for errors and omissions. The provision of this information should not be construed as a recommendation to use any of our products in violation of any patent rights or breach of any statute or regulation. Users are advised to make their own determination as to the suitability of this information in relation to their particular purposes and specific circumstances. Since the information contained in this document may be applied under condition beyond our control, we can accept no responsibility for any loss or damage caused by any person acting or refraining from action as a result of this information.