# Decorative Wall & Ceiling Linings

# **PRODUCT DATA SHEET**



# **GENERAL PURPOSE INTERIOR**



#### **Products include:**

easyVJ, easyGROOVE, easyREGENCY, easyASCOT classic/vogue, easyLINING & expression series.

Easycraft General Purpose Interior panels are made from a moisture resistant medium density fibreboard (MDF) suitable for interior wall & ceiling linings. The moisture resistant properties are due to the bonding of the wood fibres with a specially formulated moisture resistant resin system. It is a wood based product and reacts to changes in moisture like a natural timber, ie. high or low humidity may cause some expansion or contraction without any degradation to the strength of the board.

#### **APPLICATIONS**

Easycraft General Purpose Interior is designed for INTERIOR walls & ceiling linings.

#### **SHEET SIZES & THICKNESS**

Easycraft General Purpose Interior is available in a large range of thickness and sheet sizes.

#### FIRE HAZARD INDICES

(Typically achieved when tested to AS/NZS 1530.3)

(Typically achieved when tested to AS/NZS 1330.3)				
Indices	Result	Range		
Ignitability	14	0-20		
Spread of Flame	8	0-10		
Heat Evolved	7	0-10		
Smoke Developed	4	0-10		

#### **FIRE TEST RESULTS**

Cone Calorimeter (Results when tested in accordance with AS/NZS 3837)

Classification	Result	
Group Number	3	
Average Specific Extinction Area	47.0 Kg/m <sup>2</sup>	

#### **PROPERTIES**

(Typical physical properties when tested to AS/NZS 1859.2)

	THICKNESS				
Specifications	Unit	9-12mm	13-22mm		
Thickness Tolerance	mm	+/-0.2	+/-0.3		
Board Density	kg/m³	760	730		
Internal Bond	MPa	1.00	0.90		
Modulus of Rupture	MPa	46.0	43.0		
Modulus of Elasticity	MPa	3600	3600		
Surface Soundness	MPa	1.3	1.7		
Screw Holding - Face	N		≥700		
Screw Holding - Edge	N		≥1100		
Thickness Swell (24hr)	%	<7	<4		
Wet Bending Strength (Method A)	MPa	10.5	9.7		
Formaldehyde level	mg/L	≤0.5	≤0.5		

## THERMAL PROPERTIES

The thermal conductivity of MDF varies slightly with thickness with the usual range being 0.05 - 0.08 kcal/mh°C (0.12 - 0.15 W/m°K) Like natural timber, MDF has a low thermal capacity. With the normal range of temperature variation, MDF is dimensionally stable and it's strength unaffected.

### CONTACT

For further information on this product, contact:

Australian Panels Pty Ltd (ABN 31 003 246 357)

Address 2 Wella Way Somersby NSW 2250 Australia

**Telephone** 1300 300 547 **Fax** 1300 320 547

Whilst the information contained in this document is based on data which, to the best of our knowledge, was accurate and reliable at the time of preparation, we can accept no responsibility for errors and omissions. The provision of this information should not be construed as a recommendation to use any of our products in violation of any patent rights or breach of any statute or regulation. Users are advised to make their own determination as to the suitability of this information in relation to their particular purposes and specific circumstances. Since the information contained in this document may be applied under condition beyond our control, we can accept no responsibility for any loss or damage caused by any person acting or refraining from action as a result of this information.